

Beryllium Copper Brush Alloy 25 C172000

- Temper: 1/2 H
- Density: .298 lb/in<sup>3</sup> (8.25 g/cm<sup>3</sup>)
- Yield Strength (0.2% offset): 75-95 ksi (52-67 kg/mm<sup>2</sup>)
- Ultimate Tensile Strength: 85-100 ksi (59-71 kg/mm<sup>2</sup>)
- Thermal Conductivity: 50 BTU/ft.hr.F (85 W/m.K)